

Nouryon

Bermocoll® 产品线



00176_080219

涂料级别	产品名称	粘度 (mPa·s)*	
		1% 溶液	2% 溶液
常规型	Bermocoll E 230 FQ		260–360
	Bermocoll E 320 FQ		1850–2650
	Bermocoll EM 7000 FQ	6000–8000	
生物稳定型	Bermocoll EBS 351 FQ		5000–6000
	Bermocoll EBS 451 FQ	3000–4000	
	Bermocoll EBS 481 FQ	4000–6000	
	Bermocoll EBM 3000	2000–3000	
	Bermocoll EBM 5500	5000–6500	
	Bermocoll EBM 8000	7000–9000	
	Bermocoll EBM 10000	10000–15000	
高性能型	Bermocoll Prime 1000	500–900	
	Bermocoll Prime 1500	900–1500	
	Bermocoll Prime 2500	2200–3200	
	Bermocoll Prime 3500	3000–4000	
缔合型	Bermocoll EHM 200	350–700	
	Bermocoll EHM 300	1700–3000	
	Bermocoll EHM 500	7000–10000	
高性能缔合型	Bermocoll EHM EXTRA	250–450	
Bermocell	Bermocell 25K2	3000–4000	
	Bermocell 100K2	>10000	

* 粘度测试方法：在 20°C (68°F) 的水溶液中使用 Brookfield LV 粘度计，测试转速设定为 12 rpm。