

Structure 2020 polymer

ASE rheology modifier

Structure 2020 is an acrylate based emulsion copolymer.

INCI name

Acrylates Crosspolymer-6

Specifications

pH	2.2-3
Solid content	29-31 %
Viscosity	10000-15000 (pH 9.0, NaOH, 25°C, 10 rpm, 2.5% (dry)) cps

Characteristics

Appearance	White Emulsion at 20°C
Density	8.82 lbs/US gal. at 25°C
Specific Gravity	1.06 g/cc at 25°C
Viscosity	≤200 cps at 25°C

Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

Storage

Structure 2020 is available in bulk, intermediate bulk and 55-gallon drums. Storage tanks should be plastic, fiberglass, or 316 stainless. Pumps should be low-shear type, such as diaphragm or peristaltic type with all wetted parts and lines being stainless steel, plastic or Teflon®. Mild steel, copper, brass and aluminum should not be used. Filtering should be under low shear and volume flow conditions. Freezing should be avoided as it destabilizes the emulsion. The recommended storage temperature is 5-50°C (40-120°F). Dilution or pH adjustment of the product may require additional preservative to prevent biological growth. Keep containers tightly sealed to prevent emulsion from air drying and forming a film. Teflon® is a registered trademark of E.I. DuPont De Nemours & Co.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

STRUCTURE is a registered trademark in many countries.

Contact Us

USA and Canada

Global Headquarters
Chicago
USA
+1 312 544 7000
ansc-cs@nouryon.com

China

Regional Headquarters
Shanghai
China
+86 21 2220 5000
surfactants.asia@nouryon.com

Europe

Regional Headquarters
Stenungsund
Sweden
+46 303 850 00
surfactants.europe@nouryon.com

South East Asia

Regional Headquarters
Singapore
+65 6635 5183
surfactants.asia@nouryon.com

South America

Regional Sales Office
Itupeva
Brazil
+55 11 4591 8938

The Nouryon logo consists of the word "Nouryon" in a bold, orange, sans-serif font. The letter "N" is stylized with a white negative space cutout.