

Witbreak DRB-127

Oxyalkylated Resin

Nonionic resin oxyalkylate water in oil demulsifier

Specifications

Appearance	Dark amber liquid at 25°C
Moisture	≤ 0.20 %
Relative Solubility Number	8.5-8.9
Solid content	48.0-52.0 %

Characteristics

Brookfield viscosity, 77°F	9250 cps
Density	8.2 Lbs/Gal at 25°C
Flash point	30 C
Moisture	≤ 0.5 %
Odor	Bland
pH	10 (5% in 3:1 IPA/H20)
Pour point	-9 ℃
Relative Solubility Number	8.9
Solubility: 10% in Aromatic 150	Soluble
Solubility: 10% in Isopropyl Alcohol	Soluble
Solubility: 10% in Kerosene	Dispersible
Solubility: 10% in Water	Insoluble
Solubility: 10% in Xylene	Soluble
Solubility: 50% in Aromatic 150	Soluble
Solubility: 50% in Isopropyl Alcohol	Soluble
Solubility: 50% in Kerosene	Soluble
Solubility: 50% in Water	Insoluble
Solubility: 50% in Xylene	Soluble

Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

WITBREAK is a registered trademark in many countries. For more information, please visit our website at www.nouryon.com.

